

(19)



Europäisches Patentamt

European Patent Office

Office européen des brevets



(11)

**EP 0 709 390 B1**

(12)

## EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention  
of the grant of the patent:  
15.11.2000 Bulletin 2000/46

(51) Int Cl.7: **C07F 7/14**, C07F 7/18,  
C07F 7/08

(21) Application number: 95307517.3

(22) Date of filing: 23.10.1995

(54) **Unsaturated ketones as accelerators for hydrosilylation**

Ungesättigte Ketonen als Hydrosilylierungsbeschleuniger

Cétones insaturées comme accélérateur d'hydrosilylation

(84) Designated Contracting States:  
DE FR GB

(30) Priority: 27.10.1994 US 329819

(43) Date of publication of application:  
01.05.1996 Bulletin 1996/18

(73) Proprietor: **DOW CORNING CORPORATION**  
Midland, Michigan 48686-0995 (US)

(72) Inventors:  
• **Bank, Howard Marvin**  
Freeland, Michigan (US)

• **Decker, Gary Thomas**  
Midland, Michigan (US)

(74) Representative: **Spott, Gottfried, Dr. et al**  
**Spott & Weinmiller**  
Patentanwälte  
Sendlinger-Tor-Platz 11  
80336 München (DE)

(56) References cited:  
EP-A- 0 460 589 EP-A- 0 602 922

BEST AVAILABLE COPY

EP 0 709 390 B1

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

## Description

[0001] The present invention is a hydrosilation process where a silicon hydride is reacted with an unsaturated reactant in the presence of a platinum catalyst and an unsaturated ketone accelerator. Such accelerators are especially useful for the hydrosilation of unsaturated reactants where the unsaturation is in the internal portion of the compound's structure, for example, as in cyclopentene and cyclohexene. These accelerators are effective in the absence of oxygen activation of the platinum catalyst and are surprisingly synergetic with oxygen activation of platinum catalyst.

[0002] It is known in the art to produce organosilicon compounds by reacting a compound containing silicon hydride with an unsaturated organic compound in the presence of a catalyst. This reaction is usually referred to as hydrosilation or hydrosilylation. Typically the catalyst is platinum metal on a support, a platinum compound generally in a solvent or a platinum complex.

[0003] In U.S. Patent 2,823,218, a method is taught for the production of organosilicon compounds by reacting an Si-H with a compound containing aliphatic carbon atoms linked by multiple bonds in the presence of chloroplatinic acid. U.S. Patent 3,220,972 shows a similar process, however, the catalyst is a reaction product of chloroplatinic acid.


[0004] One of the major problems known in the art for hydrosilation reactions is the deactivation of the catalyst prior to the completion of the reaction. One method for catalyst reactivation has been to expose the reaction mixture to oxygen. For example, U.S. Patent 4,578,497, claims the use of an oxygenated platinum catalyst for use in hydrosilating alkylsilanes. EP Patent Application 0533170A1, discloses a method for controlling hydrosilation reaction mixtures by controlling the solution concentration of oxygen relative to the platinum present in the reaction mixture.

[0005] In addition to the deactivation problem of the platinum catalyst, hydrosilation processes taught in the art are not particularly effective in hydrosilating internal unsaturated bonds in organic compounds. We have unexpectedly found that unsaturated ketones will act as accelerators for platinum-catalyzed hydrosilation processes. The unsaturated ketone accelerators also improve yield of the process in the presence or absence of oxygen. They are particularly effective in facilitating the hydrosilation of internal unsaturated bonds of organic compounds.

[0006] The present invention is a hydrosilation process which comprises contacting (A) a silicon hydride described by formula  $R^1_a H_b SiCl_{4-a-b}$  (1) where each  $R^1$  is independently selected from a group consisting of alkyls comprising one to 12 carbon atoms, cycloalkyls comprising four to 12 carbon atoms and aryls;  $a=0$  to 3,  $b=1$  to 3 and  $a+b=1$  to 4; and (B) an unsaturated reactant selected from a group consisting of (i) substituted and unsubstituted unsaturated organic compounds or mixtures thereof (ii) silicon compounds comprising substituted or unsubstituted unsaturated organic substituents, and (iii) mixtures of (i) and (ii); in the presence of a catalyst selected from platinum compounds or platinum complexes and an accelerator selected from unsaturated ketones described by formulas



or



where  $R^2$  is selected from alkyls comprising one to 12 carbon atoms, each  $R^3$  is independently selected from hydrogen atom or alkyls comprising one to four carbon atoms,  $R^4$  is selected from hydrogen atom or non-aryl monovalent hydrocarbon radicals comprising one to 12 carbon atoms,  $n=0$  to 4 and  $m=1$  to 17.

[0007] The contacting of the silicon hydride with the unsaturated reactant is effected in standard type reactors for conducting hydrosilation processes. The contact and reaction may be run as a continuous, semi-continuous or batch reaction.

[0008] Silicon hydrides which are useful in the present process are described by formula (I), where each  $R^1$  is independently selected from a group consisting of alkyls comprising one to 12 carbon atoms, cycloalkyls comprising four to 12 carbon atoms and aryls;  $a=0$  to 3,  $b=1$  to 3 and  $a+b=1$  to 4.  $R^1$  can be a substituted or unsubstituted alkyl, cycloalkyl or aryl as described.

[0009] In formula (1), it is preferred that each  $R^1$  be independently selected from alkyls comprising one to six carbon atoms. Even more preferred is when each  $R^1$  is methyl. Examples, of silicon hydrides described by formula (1) which are useful in our process include trimethylsilane, dimethylsilane, triethylsilane, dichlorosilane, trichlorosilane, methyl-dichlorosilane, dimethylchlorosilane, ethyldichlorosilane, cyclopentyldichlorosilane, methylphenylchlorosilane and (3,3,3-trifluoropropyl)-dichlorosilane. Examples of preferred silicon hydrides described by formula (1) include methyl-dichlorosilane and dichlorosilane.

**[0010]** The silicon hydride is contacted with an unsaturated reactant selected from a group consisting of (i) substituted and unsubstituted unsaturated organic compounds or mixtures thereof, (ii) silicon compounds comprising substituted and unsubstituted unsaturated organic substituents, and (iii) mixtures of (i) and (ii). For this invention, "unsaturated" means that the compound contains at least one carbon-carbon double bond.

**[0011]** More specific examples of the unsaturated reactants useful in this process include unsubstituted cycloalkene compounds comprising at least four carbon atoms, substituted cycloalkene compounds comprising at least 4 carbon atoms, linear alkene compounds comprising two to 30 carbon atoms, branched alkene compounds comprising four to 30 carbon atoms and mixtures of two or more of any of the above.

**[0012]** The substituted and unsubstituted cycloalkene compounds useful in the present process are those containing one or more unsaturated carbon-carbon bonds in the ring. The unsubstituted cycloalkene compounds are, for example, cyclobutene, cyclopentene, cyclohexene, cycloheptene, cyclooctene, cyclopentadiene, 1,3-cyclohexadiene and 1,3,5-cycloheptatriene. Substituted unsaturated compounds useful in our invention are 3-methylcyclopentene, 3-chlorocyclobutene, 4-phenylcyclohexene and 3-methylcyclopentadiene. The preferred cycloalkene compounds are cyclohexene and cyclopentene, with cyclohexene being the most preferred.




**[0013]** Other unsaturated organic compounds useful in our claimed process are linear and branched alkenyl compounds including, for example, compounds with terminal unsaturation such as 1-hexene and 1,5-hexadiene, compounds with internal unsaturation such as trans-2-hexene and unsaturated aryl containing compounds such as styrene and  $\alpha$ -methylstyrene.

**[0014]** The unsaturated reactants may also comprise halogen, oxygen in the form of acids, anhydrides, alcohols, esters, ethers and nitrogen. Two or more of the described unsaturated organic compounds may be used in the present process.


**[0015]** The unsaturated organic compounds comprising halogen include vinyl chloride, allyl chloride, allyl bromide, allyl iodide, allyl bromide, methallyl chloride, trichloroethylene, tetrachloroethylene, tetrafluoroethylene, chloroprene, vinylidene chloride and dichlorostyrene.

**[0016]** Suitable unsaturated organic compounds comprising oxygen include ethers such as allyl and vinyl ethers; alcohols such as allyl alcohol (vinyl carbinol), methylvinylcarbinol and ethynyldimethyl-carbinol; acids such as acrylic, methacrylic, vinylacetic, oleic, sorbic and linolenic; and esters such as vinyl acetate, allyl acetate, butenyl acetate, allyl stearate, methylacrylate, ethylcrotonate, diallyl succinate and diallyl phthalate. Suitable nitrogen containing unsaturated organic compounds are indigo, indole, acrylonitrile and allyl cyanide.

**[0017]** Specifically included within the definition of unsaturated organic compounds are those substituted by organofunctional moieties such as  $\text{CH}_2=\text{CHCH}_2\text{OC}(\text{O})\text{C}(\text{CH}_3)=\text{CH}_2$ ,  $\text{CH}_2=\text{CHCH}_2\text{NHCH}_2\text{CH}_2\text{NH}_2$ ,  $\text{CH}_2=\text{CHCH}_2\text{NH}_2$ ,



**[0018]** The unsaturated organic compound is a silicon compound comprising substituted or unsubstituted organic substituents as described by the formulas:



**[0019]** Prior to contact of the silicon hydride with the unsaturated reactant, it may be preferable to treat or purify the unsaturated reactant. Useful methods are those known in the art for treating or purifying unsaturated organic compounds and include distillation or treatment with an adsorbent such as alumina or molecular sieves.

**[0020]** The relative amounts of silicon hydride and unsaturated reactant used in the present process can be varied within wide limits. Although one unsaturated carbon-carbon linkage per silicon-bonded hydrogen atom is stoichiometric, there is no specific requirement that our process be run under stoichiometric conditions. Generally, it is preferred that the process be run with a stoichiometric excess of silicon hydride. Preferred is when our process is run with 0.1 to ten percent stoichiometric excess of the silicon hydride.

**[0021]** The silicon hydride and unsaturated reactant are contacted in the presence of a catalyst selected from platinum compounds or platinum complexes. Any platinum containing material which effects the reaction between the silicon hydride and an unsaturated carbon-carbon bond of the unsaturated organic compound is useful in the present invention. Examples of useful platinum catalysts are described in U.S. Patents 4,578,497; 3,220,972 and 2,823,218.

**[0022]** The catalyst can be, for example, chloroplatinic acid, chloroplatinic acid hexahydrate, Karstedt's catalyst (i.

e. a complex of chloroplatinic acid with sym-divinyltetramethyldisiloxane), dichlorobis(triphenylphosphine)-platinum(II), cis-dichloro-bis(acetonitrile)platinum(II), dicarbonyldichloroplatinum(II), platinum chloride and platinum oxide.


[0023] A preferred platinum catalyst is selected from the group consisting of chloroplatinic acid, chloroplatinic acid hexahydrate and platinum vinylsiloxane complexes such as a neutralized complex of chloroplatinic acid with divinyltetramethyldisiloxane.

[0024] Generally, those concentrations of catalyst which provide at least one mole of platinum up to one billion moles of unsaturated carbon-carbon bonds added to the process by the unsaturated reactant are useful in the present process. A preferred concentration of platinum catalyst is that providing one to 1000 moles of platinum per  $1 \times 10^6$  moles of unsaturated carbon-carbon bonds provided to the process by the unsaturated reactant.


[0025] The catalyst may be dissolved in a solvent for ease of handling and to facilitate measuring the small amounts typically needed. Suitable solvents include, for example, non-polar hydrocarbon solvents such as benzene, toluene and xylene and polar solvents such as alcohols, glycols and esters.

[0026] The present process is carried out in the presence of an unsaturated ketone accelerator described by formulas (2) and (3), where  $R^2$  is selected from alkyls comprising one to 12 carbon atoms, each  $R^3$  is independently selected from hydrogen atom or alkyls comprising one to four carbon atoms,  $R^4$  is selected from hydrogen atom or non-aryl monovalent hydrocarbon radicals comprising one to 12 carbon atoms,  $n$  is a value within a range of zero to four and  $m$  is a value within a range of one to 17. Preferred is where  $m=3$ .


[0027] The substituent  $R^2$  is, for example, methyl, ethyl, propyl, isopropyl, butyl and tertiary butyl. Preferred is when  $R^2$  is selected from methyl or ethyl. The substituent  $R^3$  is hydrogen atom or an alkyl comprising one to four carbon atoms as described for  $R^2$ . Preferred is when  $R^3$  is selected from hydrogen atom or methyl. Substituent  $R^4$  is hydrogen atom or any non-aryl monovalent hydrocarbon radical comprising one to 12 carbon atoms.  $R^4$  can be, for example, an alkyl radical such as methyl, ethyl, propyl, isopropyl, butyl, tertiary butyl, pentyl and hexyl; a cycloalkyl such as cyclopentyl and cyclohexyl; an alkenyl radical such as vinyl, allyl and pentenyl; substituted cycloalkenyls such as



or



Preferred is when  $R^4$  is selected from a group consisting of hydrogen atom, methyl,



or



radicals.

[0028] The unsaturated ketone accelerator is, for example,  $\alpha$ -ionone,  $\beta$ -ionone, 4-hexene-3-one, ethylvinylketone, 2-cyclohexene-1-one, isophorone, mesityl oxide and 5-hexene-2-one. A preferred unsaturated ketone accelerator is selected from a group consisting of  $\alpha$ -ionone,  $\beta$ -ionone, 4-hexene-3-one, ethylvinylketone, 2-cyclohexene-1-one and isophorone.

[0029] An effective concentration of the unsaturated ketone accelerator is added to the present process, where an effective concentration is one that facilitates initiation of the reaction between the silicon hydride and the unsaturated organic compound, accelerates the rate of reaction or reduces loss of reactivity of the catalyst in the process. An effective concentration of the accelerator is generally within a range of 0.01 to 20 weight percent of the weight of the unsaturated reactant. Preferred is when the accelerator is 0.1 to ten weight percent of the weight of the unsaturated reactant.

[0030] The presence of oxygen during practice of the present process will enhance reaction parameters such as the



reaction rate and selectivity of addition when the solution concentration of oxygen is controlled relative to platinum catalyst in the reaction mixture. The oxygen is added to the reaction mixture by either bubbling it into one of the reactants or by directly bubbling it into the reaction mixture. Contacting the oxygen on the surface of the liquid, such as by blowing oxygen into the vapor space of the reactor or by purging the reactor system with oxygen may also be used. However, this latter procedure may not be as effective due to mass transfer considerations.

[0031] The effective amount of oxygen added to the present process will be dependent upon such factors as the operating conditions, the reactants and the amount of catalyst present. It is preferred to introduce the oxygen into the process when combined with an inert gas at an oxygen level ranging from several parts per million up to 40 weight percent, based on the combined weights of the oxygen and inert gas. More preferred is when the oxygen is diluted in an inert gas to 0.1 to 40 weight percent. The inert gas is, for example, nitrogen or argon. Typically, the preferred amount of oxygen to be added to the process is determined by monitoring the rate of reaction and by-product formation. A process for adding oxygen to a hydrosilation process is described in U.S. Patent 5,359,111 which more fully discloses the way oxygen is used in a process like this one.

### Example 1

[0032] A variety of unsaturated ketones were evaluated for their ability to accelerate the reaction of methyldichlorosilane with cyclohexene in the presence of a platinum catalyst.

[0033] A stock mixture was prepared in an argon purged and blanketed bottle. The stock mixture comprised four molar percent excess of methyldichlorosilane in cyclohexene which had been treated with 13X molecular sieves. To the stock mixture were added  $6 \times 10^{-5}$  moles of platinum, as a complex prepared by the reaction of chloroplatinic acid with sym-divinyldimethyltetramethyldisiloxane, per mole of cyclohexene. Aliquots of this catalyzed stock solution were then transferred to argon-purged glass tubes and unsaturated ketones as listed in Table 1. The aliquots were added to individual tubes at a concentration of 1 weight percent of the cyclohexene present in the tube. The tubes were then heat sealed under argon purge and heated at 80°C. for three hours. At the end of this time, the tubes were cooled and the contents were analyzed by gas chromatography using a thermal conductivity detector (GC-TC). The results of this analysis are also reported in Table 1 as the average area percent of methyl(cyclohexyl)dichlorosilane ( $\text{MeC}_6\text{H}_{11}\text{SiCl}_2$ ) under the GC-TC trace for the number of replicate samples provided in parentheses.

Table 1

Effect of Unsaturated Ketones on Reaction of Methyldichlorosilane with Cyclohexene	
Unsaturated Ketone	Area% $\text{MeC}_6\text{H}_{11}\text{SiCl}_2$
None	33.9 (n=7)
2-Cyclohexene-1-one	82.5 (n=1)
$\alpha$ -Ionone	79.5 (n=3)
$\beta$ -Ionone	79.9 (n=3)
4-Hexene-3-one	77.0 (n=3)
Isophorone	85.3 (n=1)
Mesityl oxide	70.1 (n=2)
Ethylvinylketone	67.4 (n=3)
Trans-4-phenyl-3-butene-2-one*	32.8 (n=2)
2-Methyl-2-cyclopentene-1-one*	8.5 (n=2)

\*Not within scope of present invention.

### Example 2

[0034] The effect of oxygen on the unsaturated ketone acceleration of the reaction of methyldichlorosilane with cyclohexene in the presence of a platinum catalyst was evaluated.

[0035] A comparison run was made to evaluate the effects of oxygen in the absence of an unsaturated ketone accelerator. A dried flask was purged with a 2%  $\text{O}_2/\text{N}_2$  purge and then charged with 0.95 mole of cyclohexene which had been treated with 13X molecular sieves. To the flask were added  $1.2 \times 10^{-4}$  moles of platinum, as a complex prepared by the reaction of chloroplatinic acid with symdivinyldimethyltetramethyldisiloxane, per mole of cyclohexene. This mixture was then heated to 80°C. and 0.91 mole of methyldichlorosilane was added to the flask at a rate of 1.8 mL/min.

[0036] A sample was taken from the flask at 174 minutes and analyzed by GC-TC. The amount of methyl(cyclohexyl)dichlorosilane produced is reported in Table 2 as the area percent under the GC-TC trace.

[0037] A second run was made, as described for the comparison run, in the presence of 1 weight percent of 2-cyclohexene-1-one, based on the weight of cyclohexene. The amount of methyl(cyclohexyl)dichlorosilane produced in the presence of both oxygen and unsaturated ketone accelerator is reported in Table 2 as the area percent under the GC-TC trace.

Table 2

Effects of Oxygen and 2-Cyclohexene-1-one on Reaction of Methylchlorosilane with Cyclohexene			
Unsaturated Ketone	2%O <sub>2</sub> /N <sub>2</sub>	Time (min.)	Area% MeC <sub>6</sub> H <sub>11</sub> SiCl <sub>2</sub>
None	Yes	174	59.6
2-Cyclohexene-1-one	Yes	130	93.6

Example 3

[0038] The ability of α-ionone to accelerate the reaction of methylchlorosilane with cyclopentene in the presence of a platinum catalyst was evaluated. A platinum catalyzed stock mixture as described in Example 1 was prepared replacing the cyclohexene with cyclopentene. The mixture was reacted by the method of Example 1 for three hours at 80°C in the presence of 1 weight percent of α-ionone, based on the weight of cyclopentene. A comparison run was made without the addition of α-ionone. The results are reported in Table 3 as the area percent of methyl(cyclopentyl)dichlorosilane (MeC<sub>5</sub>H<sub>9</sub>SiCl<sub>2</sub>) under the GC-TC trace.

Table 3

Effect of Alpha-Ionone on Reaction of Methylchlorosilane With Cyclopentene	
Unsaturated Ketone	Area% MeC <sub>5</sub> H <sub>9</sub> SiCl <sub>2</sub>
None	85.6
α-Ionone	85.0

[0039] Although not evidenced by the data in Table 3, we believe the rate of reaction to be faster when α-ionone is used as an accelerator in the described reaction.

Example 4

[0040] The effect of β-ionone on the platinum catalyzed reaction of dichlorosilane with cyclopentene was evaluated. The reaction was conducted in argon-purged sealed tubes as described in Example 1. The sealed tubes contained a mixture comprising a molar ratio of dichlorosilane (H<sub>2</sub>SiCl<sub>2</sub>) to cyclopentene of 0.096 to 1.0. Then 1 x 10<sup>-4</sup> moles of platinum, complexed as described in Example 1, were added per mole of dichlorosilane. The mixture was tested in the presence and absence of 1 volume percent β-ionone, based on total volume, for the times and temperatures described in Table 4. The contents of the tubes were cooled at the end of the reaction periods and analyzed by GC-TC. The results are presented in Table 4 as the area percent under the GC-TC trace for cyclopentylchlorosilane (C<sub>5</sub>H<sub>9</sub>SiCl<sub>2</sub>) and cyclopentyltrichlorosilane (C<sub>5</sub>SiCl<sub>3</sub>).


Table 4

Effect of β-Ionone on Reaction of Dichlorosilane With Cyclopentene				
Unsaturated Ketone	Time (min.)	Temp. (°C)	Area%	
			C <sub>5</sub> H <sub>9</sub> SiCl <sub>2</sub>	C <sub>5</sub> SiCl <sub>3</sub>
None	90	120	11.2	0.0
β-Ionone	30	24	10.4	0.6
β-Ionone	60	120	11.8	0.6


Claims

1. A hydrosilation process comprising contacting (A) a silicon hydride described by formula R<sup>1</sup><sub>a</sub>H<sub>b</sub>SiCl<sub>4-a-b</sub> where each R<sup>1</sup> is independently selected from a group consisting of alkyls comprising one to 12 carbon atoms, cycloalkyls

comprising four to 12 carbon atoms and aryls;  $a=0$  to 3,  $b=1$  to 3 and  $a+b=1$  to 4; and (B) an unsaturated reactant selected from a group consisting of (i) substituted and unsubstituted unsaturated organic compounds or mixtures thereof, (ii) silicon compounds comprising substituted or unsubstituted unsaturated substituents, and (iii) mixtures of (i) and (ii); in the presence of a catalyst selected from platinum compounds or platinum complexes and an accelerator selected from unsaturated ketones described by formulas




or




where  $R^2$  is selected from alkyls comprising one to 12 carbon atoms, each  $R^3$  is independently selected from hydrogen atom or alkyls comprising one to four carbon atoms,  $R^4$  is selected from hydrogen atom or non-aryl monovalent hydrocarbon radicals comprising one to 12 carbon atoms,  $n=0$  to 4 and  $m=1$  to 17.

2. A process according to claim 1 where each  $R^1$  is independently selected from a group consisting of alkyls comprising one to six carbon atoms.
3. A process according to claim 1 where the silicon hydride is selected from methyldichlorosilane or dichlorosilane.
4. A process according to claim 1 where the unsaturated reactant is selected from cyclohexene or cyclopentene.
5. A process according to claim 1 where the process is run with a stoichiometric excess of silicon hydride.
6. A process according to claim 1 where the concentration of platinum catalyst is that providing one to 1000 moles of platinum per  $1 \times 10^6$  moles of unsaturated carbon-carbon bonds provided to the process by the unsaturated reactant.
7. A process according to claim 1 where  $R^2$  is selected from methyl or ethyl,  $R^3$  is selected from a hydrogen atom or methyl and  $R^4$  is selected from a group consisting of hydrogen atom, methyl,



and




radicals.

8. A process according to claim 1 where the unsaturated ketone is selected from a group consisting of  $\alpha$ -ionone,  $\beta$ -ionone, 4-hexene-3-one, ethylvinylketone, 2-cyclohexene-1-one and isophorone.
9. A process according to claim 1 where the concentration of the unsaturated ketone is 0.01 to 20 weight percent of the weight of the unsaturated organic compound.
10. A process according to claim 1 further comprising the presence of oxygen during contact of the silicon hydride and unsaturated reactant.
11. A process according to claim 10 where the oxygen is introduced into the process combined with an inert gas at an oxygen level of 0.1 to 40 weight percent of the combined weights of the oxygen and the inert gas.

## Patentansprüche

1. Hydrosilylierungsverfahren, das ein Inberührungbringen (A) eines Siliciumhydrids der Formel  $R^1_a H_b SiCl_{4-a-b}$ , worin jeder Rest  $R^1$  unabhängig voneinander aus Alkylresten mit 1 bis 12 Kohlenstoffatom(en), Cycloalkylresten mit 4 bis 12 Kohlenstoffatomen und Arylresten ausgewählt ist; a 0 bis 3 bedeutet, b 1 bis 3 bedeutet und a+b 1 bis 4 bedeutet, mit (B) einem ungesättigten Reaktionspartner, der aus (i) substituierten und nichtsubstituierten ungesättigten organischen Verbindungen oder Gemischen hiervon, (ii) Siliciumverbindungen mit substituierten oder unsubstituierten ungesättigten Substituenten und (iii) Gemischen aus (i) und (ii) ausgewählt ist, in Gegenwart eines Katalysators, der aus Platinverbindungen und Platinkomplexen ausgewählt ist, und eines Promotors, der aus ungesättigten Ketonen der Formeln



oder



ausgewählt ist, worin der Rest  $R^2$  aus Alkylresten mit 1 bis 12 Kohlenstoffatom(en) ausgewählt ist, jeder Rest  $R^3$  unabhängig voneinander aus einem Wasserstoffatom oder Alkylresten mit 1 bis 4 Kohlenstoffatom(en) ausgewählt ist,  $R^4$  aus einem Wasserstoffatom und einwertigen Nicht-Arylkohlenwasserstoffresten mit 1 bis 12 Kohlenstoffatom(en) ausgewählt ist, n 0 bis 4 bedeutet und m 1 bis 17 bedeutet, umfaßt.

2. Verfahren nach Anspruch 1, worin jeder Rest  $R^1$  unabhängig voneinander aus Alkylresten mit 1 bis 6 Kohlenstoffatom(en) ausgewählt ist.
3. Verfahren nach Anspruch 1, wobei das Siliciumhydrid aus Methyldichlorsilan und Dichlorsilan ausgewählt ist.
4. Verfahren nach Anspruch 1, wobei der ungesättigte Reaktionspartner aus Cyclohexen oder Cyclopenten ausgewählt ist.
5. Verfahren nach Anspruch 1, wobei das Verfahren mit einem stöchiometrischen Überschuß an Siliciumhydrid durchgeführt wird.
6. Verfahren nach Anspruch 1, wobei die Konzentration des Platinkatalysators eine Konzentration ist, die 1 bis 1000 mole Platin pro  $1 \times 10^6$  mole ungesättigte Kohlenstoff-Kohlenstoff-Bindungen, die in dem Verfahren durch den ungesättigten Reaktionspartner bereitgestellt werden, liefert.
7. Verfahren nach Anspruch 1, worin der Rest  $R^2$  aus Methyl oder Ethyl ausgewählt ist,  $R^3$  aus einem Wasserstoffatom oder Methyl ausgewählt ist und  $R^4$  aus einem Wasserstoffatom, Methyl, einem



und einem



ausgewählt ist.


8. Verfahren nach Anspruch 1, wobei das ungesättigte Keton aus  $\alpha$ -Ionon,  $\beta$ -Ionon, 4-Hexen-3-on, Ethylvinylketon, 2-Cyclohexen-1-on und Isophoron ausgewählt ist.



9. Verfahren nach Anspruch 1, wobei die Konzentration des ungesättigten Ketons 0,01 bis 20 Gew.-%, bezogen auf das Gewicht der ungesättigten organischen Verbindung, beträgt.
10. Verfahren nach Anspruch 1, das ferner die Gegenwart von Sauerstoff während des Inberührungbringens des Siliciumhydrids mit dem ungesättigten Reaktionspartner umfaßt.
11. Verfahren nach Anspruch 10, wobei der Sauerstoff in das Verfahren in Kombination mit einem Inertgas in einer Sauerstoffmenge von 0,1 bis 40 Gew.-%, bezogen auf das Gesamtgewicht aus Sauerstoff und Inertgas, eingespeist wird.

## Revendications

1. Un procédé d'hydrosilylation consistant à mettre en contact (A) un hydruure de silicium décrit par la formule  $R^1_a H_b SiCl_{4-a-b}$  où chaque  $R^1$  est choisi indépendamment dans la classe formée par les groupes alkyles comprenant 1 à 12 atomes de carbone, cycloalkyles comprenant 4 à 12 atomes de carbone et aryles ;  $a = 0$  à 3,  $b = 1$  à 3 et  $a + b = 1$  à 4 ; et (B) un corps réagissant insaturé choisi dans la classe formée par (i) les composés organiques insaturés substitués ou non substitués ou leurs mélanges, (ii) les composés siliciés comprenant des substituants insaturés substitués ou non substitués, et (iii) les mélanges de (i) et (ii) ; en présence d'un catalyseur choisi parmi les composés du platine ou les complexes du platine et d'un accélérateur choisi parmi les cétones insaturées décrites par les formules



ou



où  $R^2$  est choisi parmi les groupes alkyles comprenant 1 à 12 atomes de carbone, chaque  $R^3$  est choisi indépendamment parmi un atome d'hydrogène ou les groupes alkyles comprenant 1 à 4 atomes de carbone,  $R^4$  est choisi parmi un atome d'hydrogène ou les radicaux hydrocarbonés monovalents non aromatiques comprenant 1 à 12 atomes de carbone,  $n = 0$  à 4 et  $m = 1$  à 17.

2. Un procédé selon la revendication 1, dans lequel chaque  $R^1$  est choisi indépendamment dans la classe formée par les groupes alkyles ayant 1 à 6 atomes de carbone.


3. Un procédé selon la revendication 1, dans lequel l'hydruure de silicium est choisi parmi le méthyldichlorosilane ou le dichlorosilane.

4. Un procédé selon la revendication 1, dans lequel le corps réagissant insaturé est choisi parmi le cyclohexène ou le cyclopentène.

5. Un procédé selon la revendication 1, dans lequel le procédé est exécuté avec un excès stoechiométrique d'hydruure de silicium.

6. Un procédé selon la revendication 1, dans lequel la concentration de catalyseur au platine est celle qui fournit 1 à 1000 moles de platine pour  $1 \times 10^6$  moles de liaisons carbone-carbone insaturées introduites dans le procédé par le corps réagissant insaturé.

7. Un procédé selon la revendication 1, dans lequel  $R^2$  est choisi parmi un groupe méthyle ou éthyle,  $R^3$  est choisi parmi un atome d'hydrogène ou un groupe méthyle et  $R^4$  est choisi dans la classe formée par un atome d'hydrogène, les groupes méthyle,



5 et



10

8. Un procédé selon la revendication 1, dans lequel la cétone insaturée est choisie dans la classe formée par la  $\alpha$ -ionone, la  $\beta$ -ionone, la 4-hexène-3-one, l'éthylvinylcétone, la 2-cyclohexène-1-one et l'isophorone.

15

9. Un procédé selon la revendication 1, dans lequel la concentration de la cétone insaturée est de 0,01 à 20 pour cent en poids par rapport au poids du composé organique insaturé.

10. Un procédé selon la revendication 1, comprenant de plus la présence d'oxygène pendant la mise en contact de l'hydruure de silicium et du corps réagissant insaturé.

20

11. Un procédé selon la revendication 10, dans lequel l'oxygène est introduit dans le procédé en association avec un gaz inerte à une concentration d'oxygène de 0,1 à 40 pour cent en poids par rapport au poids total de l'oxygène et du gaz inerte.

25

30

35

40

45

50

55

**This Page is Inserted by IFW Indexing and Scanning  
Operations and is not part of the Official Record**

**BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☒ **FADED TEXT OR DRAWING**
- ☒ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☒ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☒ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** \_\_\_\_\_

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.**